

Primer 150

Product description

Primer 150 is a universal primer for porous substrates.

Properties

- Easy to apply
- Specifically for silicones and hybrid polymeres

Applications

- Primer for porous substrates
- Joint sides of expansion joints.
- Joint sides of porous materials with raised water pressure

Technical data

Base	Synthetic resins
Consistency	Liquid
Curing system	Physical drying and reaction with moisture
Drying time	ca. 60 minutes
Density	ca. 0.93 g/ml
Consumption	ca. 5 m ² /L
Application temperature	+5°C → +25°C
Flashpoint	ca. 8°C

Footnote: Skinning time and curing speed may vary depending on environmental factors such as temperature, moisture, and type of substrates.

Substrates

- Substrate condition
The surfaces must be clean, free of dust, grease, oil and rust.
- Substrate types
Most common porous building substrates.

Application method

- Application method
Apply Primer 150 with brush or roller in one covering layer. After application of Primer 150 wait minimum 1 hour and maximum 4 hours before applying any joints sealant.
- Cleaning method
Clean with White Spirit immediately after use (not cured).

Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult the packaging label and safety data sheet for more information.

Keep the area well ventilated during use and curing of the product.

Always wear gloves and goggles.



Primer 150

Packaging/Logistics

Colour: Transparent

Packaging: 500 ml alu tin

Shelf life: 12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C

Remarks

- If the maximum waiting time has passed before application of the sealant, apply a new layer of Primer 150.
- If Primer 150 is stored at higher temperatures (> 25°C), it is possible that the product becomes unusable before the due date.

This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. It is general in nature and does not constitute any liability. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application. In every case it is recommended to carry out preliminary experiments. The manufacturer reserves the right to modify products without prior notice.